



ZHEJIANG GANGLONG NEW MATERIAL CO., LTD.
MAQIAO WARP KNITTING SCIENCE & TECHNOLOGY INDUSTRIAL ZONE
HAINING ZHEJIANG CHINA
TEL: 0086-573-7768287 FAX: 0086-573-7760999

TECHNICAL DATA

| Description of commodity: PET Blockout 530gsm | | | |
|---|---|--------|---------------------------|
| ITEM | DATA | UNIT | TEST METHOD |
| Fabric | NO | | DIN EN ISO2060 |
| Construction | | inch | DIN60001 |
| Total weight | 530 | g/sq.m | DIN53352 BS3424 method5A |
| Weight of PET | 130 | g/sq.m | DIN53352 BS3424 method5B |
| Weight of PVC | 400 | g/sq.m | DIN53352 BS3424 method5B |
| Tensile strength | Warp: 900 | N/5cm | DIN53354 BS3424 method6A |
| | Weft: 800 | | |
| Tearing strength | Warp: 80 | N | DIN53356 BS3424 method 7A |
| | Weft: 70 | | |
| Adhesion | 60 | N/5cm | DIN53357 BS3425 method9B |
| Suitable temperature | -20 -----+70 | °C | DIN 53372 BS3424 method10 |
| Flame retardancy | No | | |
| Printer type: | Printable with HP, VUTEK, SCITEX, NUR, DGI, MIMAKI, ROLAND, MUTOH, SEIKO, JET-I and etc | | |

The indexes above are on average, so there will be ±5% tolerance for actual material.